
2K Gelcoat Filler 0.2 Liter w/ hardener

Technical Data Sheet

Part no	Product description
230	2K Gelcoat Filler 0.2 Liter w/ hardener

ENGLISH

Gelcoat Filler is a white 2-component polyester-based filler. For minor damage to the gelcoat layer on e.g. boats, surfboards and plastic bodies. Also works well for damage to enamel and sanitary ware. The surface must be clean, dry and sanded. The substrate must be degreased with silicone remover both before and after sanding. Component A is thoroughly mixed with 2-3% component B. Mix for a maximum of 5 min. Spending. Must be applied in thin layers with steel or rubber filler. Best working temperature 20 ° C. Tools are cleaned with a thinner. After 1 hour, the surface can be sanded. With wet sandpaper, rubbing and polish, a shiny surface can be achieved.

Color: White
Material base: Polyester
Hardener: Benzyl peroxide
Density: approx. 1.55
Fire class: 2B
Curing time: 60 minutes at 20 ° C
Flow time: 6-8 minutes at 20 ° C
Shelf life: 1 year
Packaging: 0.2 liters
SDS: 230A + 230B

DANSK

Gelcoat Filler er en hvid 2- komponent spartelmasse på polyesterbasis. Til mindre skader i gelcoatlaget på f.eks. både, surfbrætter og plastikkarosserier. Virker også udmærket til skader på emalje og sanitetsporcelæn. Underlaget skal være rent, tørt og slebet. Underlaget skal affedtes med silikonefjerner både før og efter slibning. Komponent A blandes grundigt med 2-3% komponent B. Bland maks. for 5 min. forbrug. Skal påføres i tynde lag med stål- eller gummispartel. Bedste arbejdstemperatur 20 °C. Værktøj rengøres med fortynder. Efter 1 time kan overfladen slibes. Med vådslibepapir, rubbing og polish kan der opnås en skinnende overflade.

Farve: Hvid
Materialebasis: Polyester
Hærder: Benzylperoxid
Densitet: ca. 1,55
Brandklasse: 2B
Hærdningstid: 60 minutter ved 20 °C
Flydetid: 6-8 minutter ved 20 °C
Lagringstid: 1 år
Forpakning: Dåse 0,2 liter
SDS: 230A + 230B